

501 Elasto-Brite

DESCRIPTION:

Karnak 501 Elasto-Brite is a co-polymer elastomeric, 100% acrylic emulsion coating. 501 Elasto-Brite provides excellent protection, appearance, mildew resistance, color stability, weatherability and flexibility.

USES:

501 Elasto-Brite is designed to be applied directly over built-up roof surfaces that have aged a minimum of 90 days, SBS and APP granular modified membranes and smooth surface APP membranes that have weathered a minimum of 30 days as well as metal roofs. Also for use on above grade vertical surfaces such as concrete, concrete block, brick, stucco, metal and wood. May also be used for application over applicable base coats 405 Bond-N-Shield, 406 Tru-Grip, 404 Corrosion Proof Base and 407 EPDM & SPF as a base coat for EPDM. Meets ASTM D-6083.

SURFACE PREPARATION:

Surfaces to be coated should be dry, clean, free of dirt, dust, grease, oil and loose paint. Power wash surfaces with TSP substitute and water. Wash roof surfaces with a minimum of 2000 psi. taking all necessary precautions to avoid damage to the roof system. Patch and repair cracks or holes with appropriate sealants or caulking materials. All wet insulation should be removed and replaced with like materials. New BUR roof surfaces must age a minimum of 90 days before coating. Newly installed cold-process, hot-applied and torched-applied modified bitumen membranes should age 30 days before coating. Allow fresh masonry to cure a minimum of 30 days before application. 501 Elasto-Brite or subsequent base coats should be dry prior to application of 501 Elasto-Brite.

APPLICATION:

Mix lightly prior to application of the coating. 501 Elasto-Brite may be applied by brush, spray equipment or roller.

BRUSH / ROLLER APPLICATION:

Brush / roller application should be done perpendicular to the first coat/ base coat for proper protection.

SPRAY APPLICATION:

Utilize a standard paint spray pump or airless spray pump. Equipment manufacturer should be consulted for more complete information. Spray application should be done with a 50% over-spray pattern.



KARNAK

330 CENTRAL AVENUE, CLARK, NJ 07066
732-388-0300 • 800-526-4236 • FAX: 732-388-9422
WEB: <http://www.karnakcorp.com>

FM1015

85

501 Elasto-Brite

COVERAGE RATE:

Apply 501 Elasto-Brite at the rate of 1.5 gallons per 100 sq. ft. per coat in a two coat application for a total coverage rate of 3 gallons per 100 sq.ft. This will achieve a dry mil thickness of 20 to 24 mils. Coverage will vary depending on the surface to be coated. Allow first coat to dry 4 to 12 hours before application of the second coat. Apply when temperatures are 40°F and rising but not over 100°F. Do not apply when rain is expected during or within 24 hours after application. Read the MSDS before using. For questions regarding repairs, surface preparation or request for an MSDS, please contact Karnak Technical Services at 800-526-4236.

ARCHITECTURAL COLORS:

White and gray are standard colors. Tan, Patina Green and Terra Cotta Red are available in quantities of 210 gallons minimum.

PHYSICAL PROPERTIES:

Weight Per Gallon: 11.8 lbs.
 Solids By Weight: 65%
 Solids by Volume: 52%
 Color: White, Gray
 Hardness Shore A: 70
 Elongation: 300%
 Meets and/or exceeds ASTM D-6083
 Tensile Strength: 230 PSI
 Weathering: Excellent
 Permeability: 10 Perms
 Performance
 Service Temperature
 Range: -15°F to 180°F
 VOC: Please visit www.karnakcorp.com for latest VOC content as products are updated to comply with the most current VOC regulations

Cool Roof Rating Council (CRRC)

1. Solar Reflectance:	Initial	0.86	3 year	0.77
2. Thermal Emittance:	Initial	0.91	3 year	0.90
3. SRI:	Initial	109	3 year	96



KARNAK

330 CENTRAL AVENUE, CLARK, NJ 07066
 732-388-0300 • 800-526-4236 • FAX: 732-388-9422
 WEB: <http://www.karnakcorp.com>



501 Elasto-Brite

CAUTION:

Do not apply when rain is imminent. Coating must be dried before exposure to water. Store in a heated room and keep container covered when not in use. **Do not thin.** Keep out of reach of children. Avoid prolonged contact with skin. Dispose of in an environmentally safe manner. Cover air intakes during application and while drying.

COLD-PROCESS SYSTEMS AND COATING, EITHER EMULSION OR SOLVENT BASED, SHOULD ONLY BE INSTALLED ON DECKS WITH POSITIVE DRAINAGE. PER NRCA, (NATIONAL ROOFING CONTRACTORS ASSOCIATION) "THE CRITERIA FOR JUDGING PROPER SLOPE FOR DRAINAGE IS THAT THERE BE NO EVIDENCE OF STANDING WATER ON THE DECK 48 HOURS AFTER IT STOPS RAINING."

CARE OF TOOLS:

While material is still wet, tools may be cleaned with water. Dry coating can be cleaned with Karna-Klean or xylene or similar solvent, taking the necessary precautions when handling flammable materials.

PACKAGING:

Available in 5 gallon pails and 55 gallon drums.

If further information is needed, contact Karnak Technical Services at 1-800-526-4236.

When installed properly, this product will help reduce energy costs. Actual savings will vary based on geographical location and individual building characteristics. Consult your product manufacturer, roofing contractor, or call 1-888-STAR-YES (1-888-782-7937) for more information.

KARNAK

330 CENTRAL AVENUE, CLARK, NJ 07066
732-388-0300 • 800-526-4236 • FAX: 732-388-9422
WEB: <http://www.karnakcorp.com>

